



FIVE STAR® SPECIAL GROUT 120

Salt Resistant Precision Nonshrink Grout

PRODUCT DESCRIPTION

Five Star® Special Grout 120 is a seawater and salt resistant, cement-based, nonmetallic, nonshrink grout for applications requiring precision alignment. When tested in accordance with ASTM C 827, Five Star Special Grout 120 exhibits positive expansion. Five Star Special Grout 120 meets the performance requirements of ASTM C 1107-02 and CRD-C 621-93 specifications for nonshrink grout over a wide temperature range, 40°F - 90°F (4°C - 32°C), and a long working time, 45 minutes.

ADVANTAGES

- Air release technology
- Salt and seawater resistant
- 98% Effective Bearing Area (EBA) is typically achieved following proper grouting procedures
- Formulated with Devoider® for optimum load transfer
- Dry pack, pourable and pumpable
- Does not fall below original placement volume per ASTM C 1107
- Does not contain gas generating additives, such as aluminum powder
- Nonshrink from the time of placement
- Locally manufactured under strict quality control standards

USES

- Grouting areas subject to saltwater exposure
- Nonshrink grouting of machinery baseplates, structural steel and precast concrete in salt environments
- Installation of anchors and dowels
- Support of tanks and vessels
- Repair of concrete in confined areas

TECHNICAL SUPPORT

Five Star Products maintains the industry's foremost Technical Support Group:

- Over 50 years of experience in precision grouting
- Technical Center staffed with field experienced application specialists
- Design-A-Spec™ for engineering specification assistance
- Experienced representatives for field service
- Corporate research laboratory available to customize products for unique applications

PACKAGING AND YIELD

Five Star Special Grout 120 is packaged in heavy-duty, polyethylene lined bags containing 100 lb (45.4 kg) each, yielding approximately 0.90 cubic feet (25.5 liters) or 50 lb. (22.7 kg) yielding approximately 0.45 cubic feet (12.7 liters) of hardened material at maximum water.

SHELF LIFE

One year in original unopened packaging when stored in dry conditions. Higher humidity will reduce the shelf life.

TYPICAL PROPERTIES AT 73°F (23°C)	
Early Height Change, ASTM C 827	0.0 to 4.0%
Hardened Height Change, ASTM C 1090	0.0 to 0.3%
Effective Bearing Area	95%
Bond Strength, ASTM C 882 / 28 Days	2000 psi (13.8 MPa)
Compressive Strength, ASTM C 942 (C 109 Restrained)	
1 Day	2500 psi (17.3 MPa)
7 Days	5500 psi (38.0 MPa)
28 Days	7000 psi (48.3 MPa)

The data shown above reflect typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown above may result. Test methods are modified where applicable.



PLACEMENT GUIDELINES

1. **SURFACE PREPARATION:** All surfaces in contact with Five Star® Special Grout 120 shall be free of oil, grease, laitance and other contaminants. Concrete must be clean, sound and roughened to ensure a good bond. Soak concrete surface for 24 hours prior to application with liberal quantities of potable water, leaving the concrete saturated and free of standing water.
2. **MIXING:** Mix Five Star Special Grout 120 thoroughly for approximately five minutes to a uniform consistency with a mortar mixer. A drill and paddle mixer is acceptable for single bag mixes. For optimum performance, condition between 60°F and 80°F (15°C and 27°C). Mix Five Star Special Grout 120 with 7 to 11 quarts potable water per 100 lb. bag (3 1/2 to 5 1/2 quarts potable water per 50 lb. bag). Working time is approximately 45 minutes at 73°F (23°C). Follow printed instructions on the package.
3. **METHODS OF PLACEMENT:** Five Star Special Grout 120 may be dry packed, poured or pumped into place. Minimum placement thickness for Five Star Special Grout 120 is one inch. For pours over six inches in depth Five Star Special Grout 120 should be extended with a cleaned washed coarse aggregate meeting the requirements of ASTM C 33. Contact Five Star Technical Center at (800) 243-2206 for extension guidelines.
4. **POST-PLACEMENT PROCEDURES:** Five Star Special Grout 120 shall be wet cured for a minimum of three days, or coated with an approved curing compound after a minimum 24 hour wet cure. In-service operation may begin immediately after the required grout strength has been reached.

NOTE: PRIOR TO APPLICATION, READ ALL PRODUCT PACKAGING THOROUGHLY. For more detailed placement procedures, refer to Design-A-Spec™ or call the Five Star Products Technical Center at (800) 243-2206.

LIMITATIONS

- At time of placement, if temperatures of equipment and surfaces are not between 40°F and 90°F (4°C and 32°C), refer to Design-A-Spec™ for cold and hot weather grouting procedures.
- Never exceed the maximum water content as stated on the bag or add an amount that will cause segregation.
- For placements thinner than one inch (25 mm) or greater than six inches (150 mm), call the Five Star Products Technical Center.
- Construction practices dictate concrete foundation should achieve its design strength before grouting.
- Do not hand mix Five Star Special Grout 120.

CAUTION

Contains cementitious material and crystalline silica. International Agency for Research on Cancer has evaluated that there is sufficient evidence for the carcinogenicity of inhaled crystalline silica to humans. Take appropriate measures to avoid breathing dust. Avoid contact with eyes and contact with skin. In case of contact with eyes, immediately flush with plenty of water for at least 15 minutes. Immediately call a physician. Wash skin thoroughly after handling. Keep product out of reach of children. **PRIOR TO USE, REFER TO MATERIAL SAFETY DATA SHEET.**

For worldwide availability, additional product information and technical support, contact your local Five Star distributor, local sales representative, or you may call Five Star's Technical Center at (800) 243-2206.

WARRANTY: "FIVE STAR PRODUCTS, INC. (FSP) PRODUCTS ARE MANUFACTURED TO BE FREE OF MANUFACTURING DEFECTS AND TO MEET FSP'S CURRENT PUBLISHED PHYSICAL PROPERTIES WHEN APPLIED IN ACCORDANCE WITH FSP'S DIRECTIONS AND TESTED IN ACCORDANCE WITH ASTM AND FSP STANDARDS. HOWEVER, SHOULD THERE BE DEFECTS OF MANUFACTURING OF ANY KIND, THE SOLE RIGHT OF THE USER WILL BE TO RETURN ALL MATERIALS ALLEGED TO BE DEFECTIVE, FREIGHT PREPAID TO FSP FOR REPLACEMENT. THERE ARE NO OTHER WARRANTIES BY FSP OF ANY NATURE WHATSOEVER, EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IN CONNECTION WITH THIS PRODUCT. FSP SHALL NOT BE LIABLE FOR DAMAGES OF ANY SORT, INCLUDING PUNITIVE, ACTUAL, REMOTE OR CONSEQUENTIAL DAMAGES, RESULTING FROM ANY CLAIMS OF BREACH OF CONTRACT, BREACH OF ANY WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FROM ANY OTHER CAUSE WHATSOEVER. FSP SHALL ALSO NOT BE RESPONSIBLE FOR USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT HELD BY OTHERS."



**Five Star Products, Inc.
Corporate Headquarters**

750 Commerce Drive
Fairfield, CT 06825
Tel: 203-336-7900
Fax: 203-336-7930
<http://www.fivestarprouducts.com>



American Owned & Operated

©2008 Five Star Products, Inc.

Revision Date: 05/08