



FIVE STAR[®] DP EPOXY GROUT PG

Low Exotherm, Pumpable Precision Grout

PRODUCT DESCRIPTION

Five Star DP Epoxy Grout PG is the only pumpable, expansive, nonshrink, low exotherm epoxy system for machinery grouting. This versatile, dual-purpose product is formulated for single, large volume placements and may be used as thin as ½ inch (13 mm) in depth. Five Star DP Epoxy Grout PG is a three component, 100% solids, solvent-free system formulated to provide high strength and superior creep resistance combined with the highest effective bearing area. Five Star DP Epoxy Grout PG exhibits positive expansion when tested in accordance with ASTM C 827.

ADVANTAGES

- Pumpable
- Permanent support for machinery requiring precision alignment
- Low exotherm with early strength development
- Long working time
- Solvent-free clean up
- Adjustable flow for various conditions
- Expansive, nonshrink, ASTM C 827
- Superior creep resistance
- Chemically resistant
- 95% Effective Bearing Area (EBA)
- Adhesion to steel

USES

- Large volume applications
- Foundation rebuilds and skid mounted equipment
- Precision alignment under dynamic load conditions
- Vibration dampening for rotating equipment
- Support of chemical tanks, vessels and rotating equipment
- Aggressive chemical environments
- Installation of anchors and dowels

PACKAGING AND YIELD

Five Star DP Epoxy Grout PG is a three component system consisting of partially filled containers of resin, hardener and polyethylene lined bags of aggregate. Available in units yielding approximately 1.85 cubic feet (52.4 liters) of hardened material when using five bags of aggregate (Standard). When maximum flow is required, up to one bag of aggregate can be withheld to enhance flow (High Flow) which reduces yield to approximately 1.58 cubic feet (44.7 liters) of hardened material.

SHELF LIFE

Two years in original unopened packaging when stored in dry conditions. Before use and for optimum performance, condition material to between 70°F and 90°F (21°C and 32°C).

TYPICAL PROPERTIES AT 73°F (23°C)		
	DP Epoxy Grout PG (Standard)	DP Epoxy Grout PG (High Flow)
Aggregate Content	5 Bags / Unit	4 Bags / Unit
Clearances	1/2 to 9 inches (13 - 229 mm)	1/2 to 6 inches (13 - 150 mm)
Height Change, ASTM C 827, at 90°F (32°C)	Positive Expansion	Positive Expansion
Effective Bearing Area	95%	95%
Creep, ASTM C 1181, 1 year 400 psi (2.8 MPa) 140°F (60°C)	4.0 x 10 ⁻³ in/in (mm/mm)	4.5 x 10 ⁻³ in/in (mm/mm)
Tensile Strength, ASTM C 307	2300 psi (15.9 MPa)	2300 psi (15.9 MPa)
Flexural Strength, ASTM C 580	4500 psi (31.0 MPa)	5000 psi (34.5 MPa)
Coefficient of Expansion, ASTM C 531	20 x 10 ⁻⁶ in/in/°F (36 x 10 ⁻⁶ mm/mm/°C)	22 x 10 ⁻⁶ in/in/°F (40 x 10 ⁻⁶ mm/mm/°C)
Bond to Concrete, ASTM C 882	Concrete Failure	Concrete Failure

Compressive Strength ASTM C 579 B*	Standard Compressive Strength psi (MPa)	Standard Compressive Modulus psi (MPa)	High Flow Compressive Strength psi (MPa)	High Flow Compressive Modulus psi (MPa)
1 Day	10000 (69.0)	1.4 x 10 ⁶ (9.7 x 10 ³)	9000 (62.1)	1.2 x 10 ⁶ (8.3 x 10 ³)
7 Days	14000 (96.6)	1.7 x 10 ⁶ (11.7 x 10 ³)	13000 (89.7)	1.5 x 10 ⁶ (10.3 x 10 ³)
Post cured at 140°F (60°C)	16500 (113.8)	1.8 x 10 ⁶ (12.4 x 10 ³)	15500 (106.9)	1.7 x 10 ⁶ (11.7 x 10 ³)

*Materials tested per ASTM C 579 B. Rate of loading 0.25 inches per minute. The data shown above reflect typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown above may result. Test methods are modified where applicable.



PLACEMENT GUIDELINES

SURFACE PREPARATION: All surfaces to be in contact with Five Star® DP Epoxy Grout PG shall be free of oil, grease, laitance and other contaminants. Concrete must be clean, sound, dry and roughened to ensure a good bond. An SSPC-SP6 commercial finish on all metal surfaces will optimize bond development to steel.

FORMS AND ISOLATION JOINTS: Formwork shall be constructed of rigid nonabsorbent materials, securely anchored, liquid tight and strong enough to resist forces developed during grout placement. The clearance between formwork and baseplate shall be three to five inches (75 to 125 mm) to allow for headbox. The clearance for remaining sides shall be one to two inches (25 to 50 mm). Areas where bond is not desired must be treated with paste wax or polyethylene. Isolation joints may be necessary depending on pour dimensions.

AGGREGATE CONTENT: Maximum aggregate content of Five Star DP Epoxy Grout PG should be used whenever possible. For increased flowability in cold temperatures, tight clearances or long flow distances, aggregate content may be reduced to four bags per unit.

MIXING: For optimum performance, all components should be conditioned to between 70°F and 80°F (21°C and 27°C) prior to use. Pour all Component B (hardener) into pail containing Component A (resin). Mix thoroughly by hand with paddle or slow speed mixer to avoid air entrapment. Pour mixed liquids into mortar mixer. While mixing, slowly add Component C (aggregate) and mix only until aggregate is completely wet. Add Component C (aggregate) immediately after mixing Component A (resin) and Component B (hardener). High flow material may be mixed with heavy duty drill. Working time is approximately 90 minutes when temperatures are at 73°F (23°C).

METHODS OF PLACEMENT: Five Star DP Epoxy Grout PG may be pumped or poured into place. All grouting shall be placed from one side to the other, maintaining contact with the bottom of the baseplate at all times. For clearances greater than nine inches (229 mm) or volumes more than 50 cubic feet (1.4 cubic meter), call the Five Star Products Technical Center at (800) 243-2206.

POST-PLACEMENT PROCEDURES: Final finishing of exposed surfaces is aided by using a solvent wiped trowel just before material becomes unworkable. In-service operation may begin immediately after minimum required grout strength and modulus have been achieved.

CLEAN UP: All tools and equipment may be cleaned with a water and strong detergent solution or solvent before material hardens. Sand may be used as an abrasive.

NOTE: PRIOR TO APPLICATION, READ ALL PRODUCT PACKAGING THOROUGHLY. For more detailed placement procedures, refer to Design-A-Spec™ or call the Five Star Products Technical Center at (800) 243-2206.

LIMITATIONS

- Flowability and strength gain are adversely affected by lower temperatures.
- For placement temperatures between 50°F and 70°F (10°C and 21°C) or above 90°F (32°C), refer to Design-A-Spec™.
- To obtain bond, concrete must be free of visible surface moisture.
- When clearances are outside the recommended range or when exceeding maximum placement volumes, contact the Five Star Products Technical Center.
- Do not add solvents to increase flowability.
- For continuous operating temperatures exceeding 180°F (82°C), contact the Five Star Products Technical Center.
- Construction practices dictate concrete foundation should achieve its design strength before grouting.

CAUTION

Irritant, toxic, strong sensitizer. Contains epoxy resin and amine. This product may cause skin irritation. Do not inhale vapors. Provide adequate ventilation. Protect against contact with skin and eyes. Wear rubber gloves, long sleeve shirt, goggles with side shields. In case of contact with eyes, flush repeatedly with water and contact a physician. Areas of skin contact should be promptly washed with soap and water. Do not take internally. Keep product out of reach of children. PRIOR TO USE, REFER TO MATERIAL SAFETY DATA SHEET.

For worldwide availability, additional product information and technical support, contact your local Five Star distributor, local sales representative, or you may call Five Star's Technical Center at (800) 243-2206.



Five Star Products, Inc.
Corporate Headquarters
750 Commerce Drive
Fairfield, CT 06825
Tel: 203-336-7900
Fax: 203-336-7930
<http://www.fivestarproducts.com>

WARRANTY: "FIVE STAR PRODUCTS, INC. (FSP) PRODUCTS ARE MANUFACTURED TO BE FREE OF MANUFACTURING DEFECTS AND TO MEET FSP'S CURRENT PUBLISHED PHYSICAL PROPERTIES WHEN APPLIED IN ACCORDANCE WITH FSP'S DIRECTIONS AND TESTED IN ACCORDANCE WITH ASTM AND FSP STANDARDS. HOWEVER, SHOULD THERE BE DEFECTS OF MANUFACTURING OF ANY KIND, THE SOLE RIGHT OF THE USER WILL BE TO RETURN ALL MATERIALS ALLEGED TO BE DEFECTIVE, FREIGHT PREPAID TO FSP FOR REPLACEMENT. THERE ARE NO OTHER WARRANTIES BY FSP OF ANY NATURE WHATSOEVER, EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IN CONNECTION WITH THIS PRODUCT. FSP SHALL NOT BE LIABLE FOR DAMAGES OF ANY SORT, INCLUDING PUNITIVE, ACTUAL, REMOTE OR CONSEQUENTIAL DAMAGES, RESULTING FROM ANY CLAIMS OF BREACH OF CONTRACT, BREACH OF ANY WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FROM ANY OTHER CAUSE WHATSOEVER. FSP SHALL ALSO NOT BE RESPONSIBLE FOR USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT HELD BY OTHERS."



American Owned & Operated

©2008 Five Star Products, Inc.

Revision Date: 05/08