



RAPID REPAIR V/O

Vertical/Overhead Concrete Repair

PRODUCT DESCRIPTION

Five Star® Rapid Repair V/O is a one component, fast setting, easy to use, enhanced repair mortar used for repair of vertical and overhead concrete surfaces without formwork. Five Star Rapid Repair V/O provides a permanent durable repair with high bond strengths and low chloride ion permeability.

ADVANTAGES



This product may be eligible for up to five LEEDS points.

- Vertical or overhead application
- One product for thick or thin applications
- Excellent freeze/thaw resistance
- One component/ease of use

USES

- Repair of concrete walls, ceilings, and other structural members

PACKAGING AND YIELD

Five Star Rapid Repair V/O is packaged in heavy-duty polyethylene lined bags weighing 50 lbs.(22.7 kg) yielding approximately 0.41 cubic feet (11.6 liters).

SHELF LIFE

One year in original unopened packaging when stored in dry conditions; high relative humidity will reduce shelf life.

TYPICAL PROPERTIES AT 70°F (21°C)	
Compressive Strength, ASTM C 109	
3 Hours	2000 psi (13.8 MPa)
1 Day	2500 psi (17.2 MPa)
7 Days	3500 psi (21.1 MPa)
28 Days	4500 psi (31.0 MPa)
Bond Strength, ASTM C 882	
1 Day	1200 psi (8.3 MPa)
7 Days	2000 psi (13.8 MPa)
Length Change, ASTM C 157	
28 Days Wet	+0.05%
28 Days Dry	-0.05%
Time of Set, ASTM C 266	
Initial Set	20 - 40 minutes
Final Set	35 - 60 minutes
Chloride Ion Permeability, ASTM C 1202	
28 Days	Very low (less than 1000 Coulombs)
Working Time at 70°F (21°C)	15 minutes

The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown above may result. Test methods are modified where applicable.

PLACEMENT GUIDELINES

- 1. SURFACE PREPARATION:** All surfaces in contact with Five Star® Rapid Repair V/O shall be free of oil, grease, laitance, and other contaminants. Concrete must be clean, sound and rough to ensure a good bond. Remove all oxidation from exposed reinforcing steel and for additional protection, coat reinforcing steel with Five Star® AC Coat. A perimeter edge and minimum depth of 1/4 inch (6 mm) should be provided for a durable repair. Featheredging is not recommended. Soak concrete surfaces prior to application with liberal quantities of potable water leaving the concrete saturated and free of standing water. Surfaces shall be conditioned to between 45°F and 90°F (7°C and 32°C) at the time of placement.
- 2. MIXING:** Pre-wet mortar mixer (stationary barrel with moving blades), empty excess water. A drill and paddle mixer is acceptable for single bag mixes. With the mixer running add minimum amount of the pre-measured potable water (total water content is 2.5 to 3.0 quarts potable water per 50 lb. unit) to the mixer. While mixing, slowly add Five Star Rapid Repair V/O and mix to a uniform non-sag consistency for two to four minutes. Adjust consistency if necessary, but do not exceed maximum water content stated on the package or an amount that will cause segregation. Do not mix more material than can be placed within 15 minutes.
- 3. METHODS OF PLACEMENT:** Firmly work a small amount of Five Star Rapid Repair V/O into damp concrete surface. Then apply additional material with trowel taking care not to leave air pockets. Application is from one side of the repair to the other, filling the repair to the desired level. Where multiple lifts are required for deep repairs, rake or scratch surface of initial lift and allow to harden for approximately 45 minutes (70°F/21°C) before applying next lift. Contact the Five Star Products Engineering and Technical Service Center at (800) 243-2206 for additional details on multiple lift applications. Finish as necessary.
SPECIAL CONDITIONS: For use in cold temperatures, Five Star Rapid Repair V/O must be maintained at a temperature of at least 45°F (7°C). Protect from freezing until a compressive strength of at least 1000 psi (6.9 MPa) is obtained. Faster strength gain will occur when the Five Star Rapid Repair V/O and mixing water have been conditioned to a higher temperature prior to placement. In hot temperatures, Five Star Rapid Repair V/O should be kept as cool as possible, but not exceeding 90°F (32°C). Chilled water should be used for mixing to help maintain sufficient working time.
- 4. POST-PLACEMENT PROCEDURES:** Five Star Rapid Repair V/O shall be protected until initial set. Immediately coat with an approved curing compound meeting water retention properties of ASTM C 309 or wet cure for a minimum of three hours. In-service operation may begin immediately after the required strength has been reached.

NOTE: PRIOR TO APPLICATION, READ ALL PRODUCT PACKAGING THOROUGHLY. For more detailed placement procedures, refer to Design-A-Spec™ installation guidelines or call the Five Star Products Engineering and Technical Service Center at (800) 243-2206.

CONSIDERATIONS

- Never exceed the maximum recommended amount of mixing water stated on the package or an amount that will cause segregation.
- Temperature of surfaces must be between 45°F and 90°F (7°C and 32°C) at time of placement.
- Repair material shall be protected from freezing until it reaches 1000 psi (6.9 MPa).

CAUTION

Contains cementitious material and crystalline silica. International Agency for Research on Cancer has evaluated that there is sufficient evidence for the carcinogenicity of inhaled crystalline silica to humans. Take appropriate measures to avoid breathing dust. Avoid contact with eyes and contact with skin. In case of contact with eyes, immediately flush with plenty of water for at least 15 minutes. Immediately call a physician. Wash skin thoroughly after handling. Keep product out of reach of children. **PRIOR TO USE, REFER TO MATERIAL SAFETY DATA SHEET.**

For worldwide availability, additional product information and technical support, contact your local Five Star distributor, local sales representative, or you may call Five Star's Engineering and Technical Service Center at (800) 243-2206.

WARRANTY: "FIVE STAR PRODUCTS INC. (FSP) PRODUCTS ARE MANUFACTURED TO BE FREE OF MANUFACTURING DEFECTS AND TO MEET FSP'S CURRENT PUBLISHED PHYSICAL PROPERTIES WHEN APPLIED IN ACCORDANCE WITH FSP'S DIRECTIONS AND TESTED IN ACCORDANCE WITH ASTM AND FSP STANDARDS. HOWEVER, SHOULD THERE BE DEFECTS OF MANUFACTURING OF ANY KIND, THE SOLE RIGHT OF THE USER WILL BE TO RETURN ALL MATERIALS ALLEGED TO BE DEFECTIVE, FREIGHT PREPAID TO FSP, FOR REPLACEMENT. THERE ARE NO OTHER WARRANTIES BY FSP OF ANY NATURE WHATSOEVER, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IN CONNECTION WITH THIS PRODUCT. FSP SHALL NOT BE LIABLE FOR DAMAGES OF ANY SORT, INCLUDING PUNITIVE, ACTUAL, REMOTE, OR CONSEQUENTIAL DAMAGES, RESULTING FROM ANY CLAIMS OF BREACH OF CONTRACT, BREACH OF ANY WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FROM ANY OTHER CAUSE WHATSOEVER. FSP SHALL ALSO NOT BE RESPONSIBLE FOR USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT HELD BY OTHERS."

Five Star Products, Inc.
Corporate Headquarters
750 Commerce Drive
Fairfield, CT 06825 USA
Tel: 203-336-7900 • Fax: 203-336-7930
<http://www.fivestarprouducts.com>



©2009 Five Star Products, Inc. (07/01/09)
American Owned & Operated