



STRUCTURAL CONCRETE® S300

Long Working Time, Permanent Repair

PRODUCT DESCRIPTION

Five Star Structural Concrete® S300 is a normal setting, one component, enhanced hydraulic cement mortar used for pourable and pumpable repairs of concrete structures. Five Star Structural Concrete® S300 may be extended with coarse aggregate for large volume repairs and foundation upgrades. Five Star Structural Concrete® S300 provides increased corrosion protection of steel reinforced structures with migrating corrosion inhibitor technology and very low chloride ion permeability.

ADVANTAGES

- Large volume repairs
- 60 minute working time
- Very low chloride ion permeability
- Pumpable
- Available in 3,000 Lb. (1,360 Kg) bulk bag packaging
- Coarse aggregate extension up to 100%
- One-day turnaround
- Outstanding corrosion resistance for protection and rehabilitation

USES

- Repair of concrete structures
- Industrial floors, slabs and overlays
- Equipment foundations
- Repair of tanks, sumps and curbs
- Ready-mix concrete truck batching
- Structural fortifications

PACKAGING AND YIELD

Five Star Structural Concrete® S300 is packaged in heavy-duty polyethylene lined bags and is available in 50 lb. (22.7 kg) units yielding approximately 0.40 cubic feet (11.3 liters) at maximum water, or 0.60 cubic feet (17.0 liters) with a 70% extension using 3/8" pea gravel. Five Star Structural Concrete® S300 is also available in 3,000 Lb. (1,360 Kg) bulk bags.

SHELF LIFE

One year in original unopened packaging when stored in dry conditions; high relative humidity will reduce shelf life.

TYPICAL PROPERTIES AT 70°F (21°C)

Compressive Strength, ASTM C 109

1 Day	3,000 psi (20.7 MPa)
3 Days	5,000 psi (34.2 MPa)
7 Days	6,500 psi (44.8 MPa)
28 Days	8,000 psi (55.2 MPa)

Bond Strength, ASTM C 882

7 Days	2,300 psi (15.9 MPa)
--------	----------------------

Time of Set, ASTM C 266

Initial Set	5 Hours (approximately)
Final Set	6 Hours (approximately)

Linear Length Change, ASTM C 157

28 Days Wet	+0.03%
28 Days Dry	-0.05%

Chloride Ion Permeability, ASTM C 1202

28 Days	Very Low (<1,000 Coulombs)
---------	----------------------------

Working Time at 70°F (21°C)	60 minutes
------------------------------------	------------

**The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown above may result. Test methods are modified where applicable.*

PLACEMENT GUIDELINES

- SURFACE PREPARATION:** All horizontal and vertical concrete surfaces in contact with Five Star Structural Concrete® S300 shall be free of oil, grease, laitance, and other contaminants. All horizontal and vertical concrete surfaces must be clean, sound and rough to ensure a good bond. Mechanically roughen concrete surfaces in accordance with ICRI Technical Guideline 310.2R to a minimum concrete surface profile roughness (CSP) 6 or greater. Remove all oxidation from exposed reinforcing steel. A perimeter edge and minimum depth of one inch (25 mm) should be provided for a durable repair. Feather edging is not desirable. Soak concrete surfaces prior to application with liberal quantities of potable water, leaving the concrete saturated and free of standing water, or use Five Star® Bonding Adhesive. Surfaces shall be conditioned to between 40°F and 90°F (5°C and 32°C) at the time of placement.
- FORMWORK:** Formwork shall be constructed of rigid non-absorbent materials, securely anchored, liquid-tight and strong enough to resist forces developed during placement. Areas where bond is not desired must be treated with form oil, paste wax or similar material. Joints may be necessary depending on pour dimensions. Any existing joints within the repair area should be maintained. Contact the Five Star Products' Engineering and Technical Service Center for further information.
- MIXING:** Wet down mortar mixer (stationary barrel with moving blades) before using and drain excess water. A drill and paddle mixer is acceptable for single bag mixes. With the mixer running add approximately 80% of the pre-measured potable water (total water content is 2¼ to 3 quarts potable water per 50 lb. unit) to the mixer. While mixing, slowly add Five Star Structural Concrete® S300 and mix to a uniform consistency for three to four minutes. Adjust consistency if necessary, but do not exceed maximum water content stated on the package or an amount that will cause segregation. Add clean, damp course aggregate meeting ASTM C 33 before final water adjustment. Do not mix more material than can be placed within 60 minutes.
- PLACEMENT PROCEDURES:** Whenever possible, place Five Star Structural Concrete® S300 full depth from one side of the repair to the other. To ensure optimal bond development, firmly work material into substrate. Placement should be continuous to prevent cold joints between pours. Finish as necessary.
SPECIAL CONDITIONS: For use in cold temperatures, Five Star Structural Concrete® S300 must be maintained at a temperature of at least 45°F (7°C). Protect from freezing until a compressive strength of at least 1,000 psi (6.9 MPa) is obtained. Faster strength gain will occur when the Five Star Structural Concrete® S300 and mixing water have been conditioned to a higher temperature prior to placement. In hot temperatures, Five Star Structural Concrete® S300 should be kept as cool as possible, but not exceeding 90°F (32°C).
- POST-PLACEMENT PROCEDURES:** Five Star Structural Concrete® S300 shall be protected from moisture loss until initial set, then immediately coated with an approved curing compound meeting water retention properties of ASTM C 309 or continuously wet cured for a minimum of three days. In-service operation may begin immediately after the required strength has been reached.

NOTE: PRIOR TO APPLICATION, READ ALL PRODUCT PACKAGING THOROUGHLY. For more detailed placement procedures, refer to Five Star® Design-A-Spec™ installation guidelines or call Five Star Products' Engineering and Technical Service Center at 1-800-243-2206.

CONSIDERATIONS

- Never exceed the maximum recommended amount of mixing water as stated on the package or add an amount that will cause segregation.
- Under high evaporative conditions, an evaporation retarder or water fogging must be used prior to curing.
- For ready-mix truck mixing guidelines, contact Five Star Products' Engineering and Technical Service Center at 1-800-243-2206.

CAUTION

Contains cementitious material and crystalline silica. International Agency for Research on Cancer has determined that there is sufficient evidence for the carcinogenicity of inhaled crystalline silica to humans. Take appropriate measures to avoid breathing dust. Avoid contact with eyes and contact with skin. In case of contact with eyes, immediately flush with plenty of water for at least 15 minutes. Immediately call a physician. Wash skin thoroughly after handling. Keep product out of reach of children. **PRIOR TO USE, REFER TO SAFETY DATA SHEET.**

For worldwide availability, additional product information and technical support, contact your local Five Star® distributor, local sales representative, or call Five Star Products' Engineering and Technical Service Center at 1-800-243-2206.

SKU / PRODUCT CODE	DESCRIPTION	# UNITS/PALLET	UNIT SIZE
28810	Five Star Structural Concrete® S300	56	50 lb. (22.7 kg) Bag

WARRANTY: "FIVE STAR PRODUCTS, INC. (FSP) PRODUCTS ARE MANUFACTURED TO BE FREE OF MANUFACTURING DEFECTS AND TO MEET FSP'S CURRENT PUBLISHED PHYSICAL PROPERTIES WHEN APPLIED IN ACCORDANCE WITH FSP'S DIRECTIONS AND TESTED IN ACCORDANCE WITH ASTM AND FSP STANDARDS. HOWEVER, SHOULD THERE BE DEFECTS OF MANUFACTURING OF ANY KIND, THE SOLE RIGHT OF THE USER WILL BE TO RETURN ALL MATERIALS ALLEGED TO BE DEFECTIVE, FREIGHT PREPAID TO FSP, FOR REPLACEMENT. THERE ARE NO OTHER WARRANTIES BY FSP OF ANY NATURE WHATSOEVER, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IN CONNECTION WITH THIS PRODUCT. FSP SHALL NOT BE LIABLE FOR DAMAGES OF ANY SORT, INCLUDING PUNITIVE, ACTUAL, REMOTE, OR CONSEQUENTIAL DAMAGES, RESULTING FROM ANY CLAIMS OF BREACH OF CONTRACT, BREACH OF ANY WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FROM ANY OTHER CAUSE WHATSOEVER. FSP SHALL ALSO NOT BE RESPONSIBLE FOR USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT HELD BY OTHERS."

Specifications Subject to Change.

For most current version of datasheet, go to FiveStarProducts.com

Five Star Products, Inc.
60 Parrott Drive
Shelton, CT 06484 USA
Tel: 203-336-7900 • Fax: 203-336-7930
FiveStarProducts.com



© 2019 Five Star Products, Inc. | 01-11-2019
12703 Rev D | American Owned & Operated

