



## Aggregate Extension Guidelines

### The following instructions apply to these Five Star® products:

- Structural Concrete®
- Structural Concrete® ES
- Structural Concrete® ES-60
- Structural Concrete® S300
- Structural Concrete® UW PG
- Highway Patch

For placements greater than 2 inches (50 mm) in depth, these products should be extended with a clean, washed, coarse aggregate meeting the requirements of ASTM C 33. Coarse aggregate size typically should not exceed 1/3 the depth of the repair.

**Mortar Mixer:** When mixing in a mortar mixer, add coarse aggregate after initial mixing of concrete repair material with mix water for 2-3 minutes. Continue mixing until coarse aggregate is uniformly wetted with repair material. Ensure larger size aggregates can be mixed properly in mortar mixer.

**Concrete Mixer:** When mixing in a concrete mixer (rotating drum mixer), add water and coarse aggregate to mixer first with mixer running followed by repair material. Concrete mixers are acceptable when extending repair material with coarse aggregate.

Depth of Pour	% By Weight Aggregate Extension (per 50 lb (22.7 kg) bag of repair material)	Actual Weight Aggregate Extension (per 50 lb (22.7 kg) bag of repair material)
Up to 2 inches (50 mm)	0%	0 lb/kg
2 to 6 inches (50-150 mm)	50%	25 lb (11.3 kg)
6 to 9 inches (150-225 mm)	60%	30 lb (13.6 kg)
9 to 12 inches (225-300 mm)	80%	40 lb (18.1 kg)
Over 12 inches (over 300 mm)	Contact Five Star Technical Support	

*Repair material yield will increase with coarse aggregate extension depending upon aggregate size, extension level, air content and specific gravity of aggregate. Typically a 50% by weight extension (by weight) will increase yield by approximately 35%. Actual yield attained in the field will vary and should be verified where greater accuracy is required.*

For information 1-800-243-2206 ▪ [FiveStarProducts.com](http://FiveStarProducts.com)

© 2021 FIVE STAR PRODUCTS, INC. | 12780 REV C

FIVE STAR TECHNICAL BULLETINS ARE PROVIDED FOR INFORMATIONAL PURPOSES ONLY AND SHOULD BE USED AS GENERAL GUIDELINES FOR CONSIDERATION BY CONTRACTORS AND ENGINEERS. WHILE EVERY REASONABLE EFFORT HAS BEEN MADE TO ENSURE THIS INFORMATION IS ACCURATE AND AUTHORITATIVE, FIVE STAR PRODUCTS DOES NOT WARRANT THE ACCURACY OR COMPLETENESS OF THIS INFORMATION, OR ITS APPROPRIATENESS FOR ANY PARTICULAR PURPOSE. THE USER OF THESE DOCUMENTS REMAINS SOLELY RESPONSIBLE FOR THE SPECIFICATION OF ALL METHODS, MATERIALS AND PRACTICES.



FIVE STAR PRODUCTS, INC.  
60 Parrott Drive  
Shelton, CT 06484 USA  
Phone: +1 203-336-7900

Build on our strength