

# REDUCE RUNWAY DOWNTIME!

RAPID SURFACE REPAIR

**EASY MIX™**

## For Airports

Runways, lighting cans and  
conduit channels

Cracks, potholes and spalls

Walkways, floors and parking lots

Control joint filler



For information 1-800-243-2206 • [FiveStarProducts.com](http://FiveStarProducts.com)



Build on our strength

RAPID SURFACE REPAIR

# EASY MIX™

Fast turnaround surface repair for roads, runways & bridges



FIVE STAR



## Innovation

- Traffic ready in as little as 30 minutes\*
- Make repairs year round - hot or cold
- No priming required to bond to concrete
- Waterproof, chemically resistant membrane protects substrates from freeze thaw spalling

Conveniently formulated for bucket mixing, this product is a self-leveling, low viscosity, two-part liquid polyurethane-hybrid polymer used to make an impact and traffic resistant polymer concrete.

When supplemented with its proprietary blended aggregate, it is used to repair and rehabilitate concrete and asphaltic pavements and can be installed at temperatures down to 0°F (-18°C). Within minutes of placement, durable, long-lasting repairs are able to handle vibration, heavy traffic, and thermal movement.

\*dependent upon air and substrate temperature



SAVE TIME AND MONEY BY  
REDUCING RUNWAY DOWNTIME

TRAFFIC READY IN 30 MINUTES\*

SIMPLE BUCKET MIX

EASY TO INSTALL

HIGH COMPRESSIVE STRENGTH

### TYPICAL PROPERTIES AT 77 °F (25 °C)

Mix Ratio by Volume	(1) Part A : (1) Part B
Viscosity @ 77 °F (25 °C) - mixed	60 cps
Gel Time, Neat	2 to 3 minutes
Working time with Aggregate	Approx. 5 minutes
Cured	
Color	Dark Grey
Cure Time (reopen to traffic)	30 minutes
Hardness, Durometer D, ASTM D-2240	70
Tensile Strength, ASTM D-412	3,000 psi (20.7 MPa)
Compressive Strength, ASTM C-579B	
1 hour	2,000 psi (13.8 MPa)
1 day	6,000 psi (41.3 MPa)
7 days	7,000 psi (48.2 MPa)
28 days	8,000 psi (55.1 MPa)
Elongation, ASTM D-638	10 - 15%
Bond Strength, ASTM C-882	2,000 psi (13.8 MPa)

SPECIFICATIONS SUBJECT TO CHANGE

#### FIVE STAR PRODUCTS, INC.

60 Parrott Drive • Shelton, CT 06484-4733 USA  
Phone: +1 203-336-7900 • Sales/Support: 1-800-243-2206  
[FiveStarProducts.com](http://FiveStarProducts.com)

© 2018 Five Star Products, Inc.  
13030 Rev B • Printed in the U.S.A.

