



FLUID GROUT 100

High Performance Precision Non-Shrink Fluid Grout

PRODUCT DESCRIPTION

Five Star® Fluid Grout 100 is the industry's leading cement-based, nonmetallic, non-shrink fluid grout for supporting machinery and equipment. It is formulated with Air Release technology that combines high performance with the greatest reliability. Five Star® Fluid Grout 100 meets the performance requirements of EN 1504-3 (Class R4) and complies with UK Specification for Highway Works Volume 1, Clause 2601. When tested in accordance with ASTM C 827, Five Star® Fluid Grout 100 exhibits positive expansion. Five Star® Fluid Grout 100 meets the performance requirements of ASTM C 1107-02 Grades A, B and C, ASTM C 1107-20 and CRD-C 621-93 specifications for non-shrink grout over a wide temperature range, 4°C - 35°C.

ADVANTAGES

- Air release technology equals controlled expansion - plastic state; dimensional stability - hardened state
- Placement within tight clearances down to 12 mm
- High 7 and 28 day strengths
- Permanent support for machinery requiring precision alignment
- Does not contain metallic gas generating additives, such as aluminum powder
- Non-shrink from the time of placement
- 95% Effective Bearing Area (EBA)
- Flowable / fluid consistency for pumping long distances

USES

- Gap clearances of 12-160 mm
- Grouting of machinery and equipment to maintain precision alignment
- Non-shrink grouting of structural steel and precast concrete
- Support of tanks and vessels

PACKAGING AND YIELD

Five Star® Fluid Grout 100 is packaged in heavy-duty, paper bags and is available in 25 kg units yielding approximately 14.1 litres of hardened material at maximum water content.

SHELF LIFE

12 months in original unopened packaging when stored in dry conditions.

TYPICAL PROPERTIES AT 20°C AT WATER ADDITION OF 5.5 L / 25Kg

Property	Test Standard	Requirement per EN1504	FSP Result	
Bond Strength	EN 1542:1999	≥ 2 MPa	2.2 MPa	
Compressive Strength	EN 12190:1999		Fluid ²	Plastic ³
	1 Day	NR	17 MPa	25 MPa
	7 Days	NR	42 MPa	50 MPa
	28 Days	≥ 45 MPa (Class R4)	55 MPa	63 MPa
Modulus of Elasticity	EN 13412	≥ 20 GPa	22 GPa	26 GPa
Thermal Compatibility	EN 13687-1:2002	≥ 2 MPa (Class R4)	Pass	
Chloride Ion Content	EN 1015-17:2000	≤ 0.05% (Class R4)	0.01%	
Carbonation Resistance	EN 13295:2005	$d_k \leq$ concrete control (Class R4)	$d_k \leq$ concrete control	
Fire Classification	EN 1504-3 Section 5.5	Declared	Euroclass A1	
Flow Between Glass Plates @ 5°C Flow Between Glass Plates @ 20°C @ 10 mm clearance	HCD Drawing No. K2	Per MCHW 2601, Part 4 (iii): Material should flow under the glass plate and rise ≥ 10 mm above the underside of the top plate at all positions, without signs of segregation, bleeding effervescence or air inclusion	PASS PASS	
Working Time @ 20°C May be affected by colder & warmer temperatures ⁴	ASTM C939 / EN 13395-1 Modified	Declared per FPC ⁵	30 minutes	

¹ NR = Not required ⁵ FPC = Factory Production Control

² 20 to 40 second flow by UK Specification for Highway Works, Vol 1, Clause 2601, Bedding Mortar, Part 4 (ii) ASTM C 939-02 (Corps of Engineers Flow Cone Method, CRD-C 611.)

³ 100% - 125% flow on flow table, CRD-C 621 (ASTM C 230, 5 drops in 3 seconds).

⁴ Refer to Five Star® Technical Bulletins: 101 *Cementitious Grouting in Cold Weather*; 102 *Cementitious Grouting in Hot Weather*

The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown may result. Test methods are modified where applicable.

APPLICATION INFORMATION

Mixing Ratio	4.5 - 5.5 L potable water per 25 kg bag	Minimum Plate Clearance	12 mm
Maximum In-Service Temperature	204°C	Placement Depth	12 mm - 160 mm >160 mm, call Five Star

PLACEMENT GUIDELINES

For optimum performance, install at temperatures between 4°C and 35°C. For hot or cold weather grouting contact Five Star Products.

- SURFACE PREPARATION:** Construction practices dictate concrete foundation should achieve its design strength before grouting. All surfaces in contact with Five Star® Fluid Grout 100 shall be clean and free of oil, grease laitance and other bond-inhibiting contaminants. To maximize bond, concrete surfaces should be prepared by acceptable means to coarse aggregate exposure. Presoak with potable water concrete surfaces for a minimum of 8 hours, continuously and consistently, via wet rags, wet hessian, ponding, or similar method to obtain a saturated surface dry (SSD) condition.
- FORMWORK:** Formwork should be constructed 24-hours prior to the pour. Formwork shall be constructed of rigid non-absorbent materials, securely anchored, liquid-tight and strong enough to resist forces developed during grout placement. The clearance between formwork and baseplate shall be sufficient to allow for a headbox to be placed between the edge of the baseplate and the form. The clearance for remaining sides shall be 25 - 50 mm. Formwork and areas where bond is not desired must be treated with form oil, paste wax or similar material. Isolation/construction joints may be necessary depending on pour dimensions.
- MIXING: Forced Action Mortar Mixer:** Start with approximately 4.5 litres of potable water per 25 kg bag in the mixer. Add Five Star® Fluid Grout 100 and mix for about 2 – 3 minutes after the addition of the final bag to a uniform consistency. Add additional potable water as necessary to achieve desired flow mixing for an additional 1 – 2 minutes after final addition of potable water. For fluid consistency, only add the amount of potable water needed to achieve a 20 – 40 second flow through a flow cone.* Do not exceed the maximum recommended amount of potable mixing water as directed or add an amount that will cause segregation.
Single Bag Mixing Drill and Paddle: Start with approximately 4.5 litres of potable water in the mix vessel. Add approximately 75-80% of Five Star® Fluid Grout 100 to the potable water and mix to uniform consistency only until grout easily wets out, then add the remaining grout and continue to mix to a uniform consistency. Add additional potable water as needed to achieve desired flow, mixing for an additional 1 – 2 minutes after final addition of potable water. For fluid consistency, only add that amount of potable water needed to achieve a 20 – 40 second flow through a flow cone.* Do not exceed the maximum recommended amount of potable mixing water as directed or add an amount that will cause segregation.
* Fluidity Test: 20 – 40 second flow through a flow cone as referenced by UK Specification for Highway Works, Vol 1, Clause 2601, Bedding Mortar, Part 4 (ii) ASTM C939-02 (Corps of Engineers Flow Cone Method, CRD-C 611).
For pours over 160 mm in depth contact Five Star Products for aggregate extension recommendations. For bulk mixing applications, contact Five Star Products.
- PLACEMENT:** Five Star® Fluid Grout 100 may be dry packed, poured, or pumped into place. Placement should always be across the shortest distance. A headbox is recommended for pouring applications. Refer to Five Star® Technical Bulletin 108 *Grout Headbox & Plunger*.
- POST-PLACEMENT PROCEDURES:** Five Star® Fluid Grout 100 shall be wet cured with potable water for a minimum of 24 hours. After initial 24-hour wet cure, grout shall be coated with an approved curing compound. If curing compound is not used, grout shall be wet cured for an additional 48 hours totaling 3 days. During the curing process, protect the grout from direct sun and wind exposure. Do not allow product to freeze until it reaches 7 MPa compressive strength. In-service operation may begin immediately after the required grout strength has been reached.

PRIOR TO APPLICATION, READ ALL PRODUCT PACKAGING THOROUGHLY. For more detailed information contact Five Star Products at +44 (0) 7469 746101.

HEALTH AND SAFETY

Contains cementitious material. May produce an allergic reaction. Take appropriate measures to avoid breathing dust. Avoid contact with eyes and contact with skin. In case of contact with eyes, immediately flush with plenty of water for at least 15 minutes. Immediately call a physician. Wash skin thoroughly after handling. Keep product out of reach of children. **PRIOR TO USE, READ THE SAFETY DATA SHEET.**

SKU/PRODUCT CODE	DESCRIPTION	#UNITS/PALLET	UNIT SIZE
25012	Five Star® Fluid Grout 100	40	25 kg
<p>WARRANTY: "FIVE STAR PRODUCTS, INC. (FSP) PRODUCTS ARE MANUFACTURED TO BE FREE OF MANUFACTURING DEFECTS AND TO MEET FSP'S CURRENT PUBLISHED PHYSICAL PROPERTIES WHEN APPLIED IN ACCORDANCE WITH FSP'S DIRECTIONS AND TESTED IN ACCORDANCE WITH ASTM AND FSP STANDARDS. HOWEVER, SHOULD THERE BE DEFECTS OF MANUFACTURING OF ANY KIND, THE SOLE RIGHT OF THE USER WILL BE TO RETURN ALL MATERIALS ALLEGED TO BE DEFECTIVE, FREIGHT PREPAID TO FSP, FOR REPLACEMENT. THERE ARE NO OTHER WARRANTIES BY FSP OF ANY NATURE WHATSOEVER, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IN CONNECTION WITH THIS PRODUCT. FSP SHALL NOT BE LIABLE FOR DAMAGES OF ANY SORT, INCLUDING PUNITIVE, ACTUAL, REMOTE, OR CONSEQUENTIAL DAMAGES, RESULTING FROM ANY CLAIMS OF BREACH OF CONTRACT, BREACH OF ANY WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FROM ANY OTHER CAUSE WHATSOEVER. FSP SHALL ALSO NOT BE RESPONSIBLE FOR USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT HELD BY OTHERS."</p>			

Five Star Products, Inc.
FiveStarProducts.com/UK

Specifications Subject to Change.
For most current version of datasheet, go to FiveStarProducts.com/UK

© 2023 Five Star Products, Inc.
uk13265eng-rG | 10-18-2023



Available in the UK through



PRECON
PRODUCTS

Tel: +44 (0) 1359 272569
E-mail: Sales@PreconProducts.co.uk