



Repair Concrete

Long Working Time, Permanent Repair

PRODUCT DESCRIPTION

Five Star® Repair Concrete is a normal setting, one component, enhanced hydraulic cement concrete repair material used for pourable and pumpable repairs of concrete structures. Five Star® Repair Concrete meets the performance requirements of EN 1504-3 (Class R4) and complies with the UK Specification for Highway Works Volume 1 Clause 5716 Repair Concrete or Mortar.

ADVANTAGES

- Large volume repairs
- 60 minute working time
- Pumpable

USES

- Repair of concrete structures
- Industrial floors, slabs, and overlays
- Equipment foundations
- Repair of tanks, sumps and curbs
- Structural fortifications

PACKAGING AND YIELD

Five Star® Repair Concrete is packaged in 25 kg bags yielding approximately 11.5 liters at maximum water.

SHELF LIFE

12 months in original unopened packaging when stored in dry conditions; high relative humidity will reduce shelf life.

TYPICAL PROPERTIES AT 20°C AT MAXIMUM WATER

Property	Test Standard	Requirement per EN 1504	FSP Result
Compressive Strength	EN 12190:1999		
	3 Day	NR ¹	35 MPa
	7 Days	NR	45 MPa
	28 days	≥ 45 MPa	65 MPa
Chloride Ion Content	EN 1015-17:2000	≤ 0.05%	< 0.01%
Bond Strength	EN 1542:1999	≥ 2 MPa	2.2 MPa
Modulus of Elasticity	EN 13412	≥ 20 GPa	40 GPa
Thermal Compatibility	EN 13687-1:2002	≥ 2 MPa	≥ 2 MPa
Carbonation Resistance	EN 13295:2005	$d_k \leq$ concrete control (Class R4)	$d_k \leq$ concrete control
Fire Classification	EN 1504.3 Section 5.5	Declared	Euroclass A1
Electrical Resistivity @ 28 Days	4-Pin Wenner Test (Spec. Clause 1770 AR Class 29F)	≥500 ≤15000 Ohm.cm	12,870 Ohm.cm
Working Time at 20°C May be affected by colder & warmer temperatures	EN 13395-1:2002	Declared per FPC ²	60 minutes

¹ NR = Not required

² FPC = Factory Production Control

The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown may result. Test methods are modified where applicable.

APPLICATION INFORMATION

Mixing Ratio 1.75 - 2.25 L potable water per 25 kg bag

Placement Depth 19 mm - 160 mm
>160 mm, contact Five Star Products

PLACEMENT GUIDELINES

For optimum performance, install at temperatures between 2°C and 35°C. For hot or cold weather applications contact Five Star Products.

- SURFACE PREPARATION:** All horizontal and vertical concrete surfaces in contact with Five Star® Repair Concrete shall be free of oil, grease, laitance, and other contaminants. A saw cut perimeter edge at 19 mm is recommended. To maximize bond, horizontal and vertical concrete surfaces should be prepared by acceptable means to coarse aggregate exposure. Remove all oxidation from exposed reinforcing steel to achieve a clean steel finish. Featheredging is not allowed.
- FORMWORK:** Formwork should be constructed 24-hours prior to the installation. Formwork shall be constructed of rigid non-absorbent materials, securely anchored, liquid-tight and strong enough to resist forces developed during placement. Formwork and areas where bond is not desired must be treated with form oil, paste wax or similar material. Joints may be necessary depending on pour dimensions. Any existing joints within the repair area should be maintained. Contact Five Star Products for further information.
- MIXING: Forced Action Mortar Mixer**
Start with approximately 1.75 litres potable water per 25 kg bag in the mixer. Add Five Star® Repair Concrete and mix for approximately 2 – 3 minutes after the addition of the final bag to a uniform consistency. Add additional potable water as necessary to achieve desired flow mixing for an additional 1 – 2 minutes after final addition of potable water. Do not exceed the maximum recommended amount of potable mixing water as directed or add an amount that will cause segregation.
Single Bag Mixing Drill and Paddle
Start with about 1.75 litres in the mix vessel. Add approximately 75-80% of Five Star® Repair Concrete to the potable mix water and mix to uniform consistency only until product easily wets out and add remaining material and continue to mix to uniform consistency. Add additional potable water as needed to achieve desired flow mixing for an additional 1 – 2 minutes after final addition of potable water. Do not exceed the maximum recommended amount of potable mixing water as directed or add an amount that will cause segregation.
For pours over 160 mm in depth contact Five Star Products for aggregate extension recommendations. For bulk mixing applications, contact Five Star Products
- METHODS OF PLACEMENT:** Whenever possible, place Five Star® Repair Concrete full depth from one side of the repair to the other. To ensure optimal bond development, firmly work material into substrate. Placement should be continuous to prevent cold joints between pours.
- POST-PLACEMENT PROCEDURES:** Keep material as cool as possible and protect from wind and sun exposure. Five Star® Repair Concrete shall be protected from moisture loss until initial set; then immediately coated with an approved curing compound or continuously wet cured for 3 days. At lower temperatures final set and strength development may take longer. Do not allow product to freeze until it reaches 7 MPa compressive strength.
- CLEAN UP:** All tools and equipment may be cleaned with soap and water before the material hardens.

NOTE: PRIOR TO APPLICATION, READ ALL PRODUCT PACKAGING THOROUGHLY. For more detailed information call Five Star Products at +44 (0) 7469 746101.

HEALTH AND SAFETY

Contains cementitious material. May cause an allergic reaction. Take appropriate measures to avoid breathing dust. Avoid contact with eyes and contact with skin. In case of contact with eyes, immediately flush with plenty of water for at least 15 minutes. Immediately call a physician. Wash skin thoroughly after handling. Keep product out of reach of children. **PRIOR TO USE, REFER TO SAFETY DATA SHEET.**

SKU / PRODUCT CODE	DESCRIPTION	# UNITS/PALLET	UNIT SIZE
28811	Five Star® Repair Concrete	40	25kg Bag

WARRANTY: "FIVE STAR PRODUCTS, INC. (FSP) PRODUCTS ARE MANUFACTURED TO BE FREE OF MANUFACTURING DEFECTS AND TO MEET FSP'S CURRENT PUBLISHED PHYSICAL PROPERTIES WHEN APPLIED IN ACCORDANCE WITH FSP'S DIRECTIONS AND TESTED IN ACCORDANCE WITH ASTM AND FSP STANDARDS. HOWEVER, SHOULD THERE BE DEFECTS OF MANUFACTURING OF ANY KIND, THE SOLE RIGHT OF THE USER WILL BE TO RETURN ALL MATERIALS ALLEGED TO BE DEFECTIVE, FREIGHT PREPAID TO FSP, FOR REPLACEMENT. THERE ARE NO OTHER WARRANTIES BY FSP OF ANY NATURE WHATSOEVER, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IN CONNECTION WITH THIS PRODUCT. FSP SHALL NOT BE LIABLE FOR DAMAGES OF ANY SORT, INCLUDING PUNITIVE, ACTUAL, REMOTE, OR CONSEQUENTIAL DAMAGES, RESULTING FROM ANY CLAIMS OF BREACH OF CONTRACT, BREACH OF ANY WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FROM ANY OTHER CAUSE WHATSOEVER. FSP SHALL ALSO NOT BE RESPONSIBLE FOR USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT HELD BY OTHERS."

Five Star Products, Inc.
FiveStarProducts.com/UK

Specifications Subject to Change.
For most current version of datasheet, go to FiveStarProducts.com/UK

© 2023 Five Star Products, Inc.
uk13313eng-rE | 10-25-23



Available in the UK through



Tel: +44 (0) 1359 272569
E-mail: Sales@PreconProducts.co.uk